



DAIKEN CORPORATION (S98FC5543C)
SINGAPORE BRANCH
100 Beach Road, #13-01/02
Shaw Tower, Singapore 189702
Tel: (65) 6297-1933 Fax: (65) 6297-1363

TO:

VINH TUONG Industrial Corporation

SEBUJECT

Test : ASTM C1185-08 for DURAFLEX Calcium Silicate Board

DESCRIPTION SAMPLE

DURAFLEX : Calcium Silicate Board

<i>Production dare</i>	<i>15th Dec</i>	<i>19th Dec</i>	<i>30th Dec</i>	<i>2nd Jan</i>	<i>9th Jan</i>
Lot No	573	583	603	606	618
Q'ty (Pcs)	10pcs	10pcs	10pcs	10pcs	10pcs

TEST RESULT

	<i>Average Level</i>	<i>5lots Average</i>	<i>Test Result</i>	<i>test method</i>
Thickness	3.5+/- 0.5	3.59	Passed	ASTM C1185-08
Length	2440+/- 6	2440.8	Passed	
Width	1210+/- 6	1210.9	Passed	
Bending (Normal)N/mM2	-	15.0	Passed	
min	Over 10	13.6		
Moisture content (%)	Less 10	6.0%	Passed	
Density (g/c)	1.2-1.45	1.37	Passed	
Water absorption rate (%)	Less 35	30.8%	Passed	
Change of dimension After absorption water (%)	Less 0.15	<i>Not complied</i>	<i>Not complied</i>	ASTM E84
Surface Burning Characteristics	-	<i>Not complied</i>	<i>Not complied</i>	

We tested DURAFLEX Calcium Silicate Board in laboratory center in Daiken Okayama factory.

Above DULAFLEX samples ware passed test method ASTM C1185-08.

Thank you.

Daiken Corporation
Singapore Branch